


UMass Amherst  
Adaptive Use Bridge Project  
Galvin Road Bridge Hardness Test Methods

Hardness data was collected on the 4 tensile coupons from the Galvin Road Bridge before they went through destructive testing. The Rockwell B test was performed in accordance to ASTM E18-03. A 1/16 inch ball indenter was used with 100 kg of test force. A total of 8 readings were taken on each specimen. The process for data collection was made uniform to increase precision. The location of the indentation for each reading is shown in Figure 1.



**Figure 1.** Hardness test locations.